

REPORT
Emission Test Chamber Study
according to COV

Product: CLIPSO IMPRIME UV
(F11002793)

Project-No.: IAL-08-0563

Order-No.: IAL-00695-11

Client: CLIPSO PRODUCTION
Monsieur Rendler
5, rue de l'église
68800 Vieux-Thann
France

Date of order: 14.07.2011

Project Manager: Diplom-Ingenieur R. Bison

Altenberge, 17.01.2011

TABLE OF CONTENTS

1	Introduction.....	3
2	Test data	3
3	Test Method	4
4	Results	5
4.1	TVOC	5
4.2	Aldehydes.....	6
5	Evaluation.....	7
5.1	Classification	7
6	Summary	8

1 Introduction

Laboratoires WESSLING S.A.R.L was contracted by CLIPSO PRODUCTION to perform an emission test chamber study of the product “CLIPSO IMPRIME UV (Lot: F11002793)” on the emissions of volatile organic compounds (VOCs) and aldehydes. The evaluation is done according to the « Arrêté du 19 avril 2011 relatif à l'étiquetage des produits de construction ou de revêtement de mur ou de sol et des peintures et vernis sur leurs émissions de polluants volatils ».

The emission chamber test was conducted in accordance with the requirements of DIN EN ISO 16000-9. The sampling was carried out according to DIN EN ISO 16000-3 / -6.

2 Test data

Product Data:	
Product: CLIPSO IMPRIME UV	Production No.: F11002793
Production Date:	Date of Reception: 30.11.2010
Packaging: Plastic	Test Period: 13.12.2010 – 10.01.2010
Test Chamber Specifications:	
Volume: 110 l – Test Chamber (Stainless Steel))	
Temperature: 23°C	Humidity: 50 % rel. humidity
Exchange Rate: 0,5 h ⁻¹	Volume Flow 917 ml/min
Loading: 0,11 m ²	Area-specific Air Exchange Rate: 0,5 m ³ /(m ² h)
Date and duration of air sampling:	
10.01.2011	Tenax: 50 min (0,1 l/min) Multisorbent: 50 min (0,1 l/min) DNPH: 200 min (0,5 l/min)

3 Test Method

The product was tested according to DIN EN ISO 16000-9 in a 110-liter test chamber made of stainless steel. The chamber was loaded on 17.01.2011. The test was designed for 28 days; the samples were taken on day 28.

The specimen was prepared according to DIN EN ISO 16000-11. 0.11 m² of the product were placed in the test chamber. The chamber was operated with a 0.5-fold change of air, a room air temperature of 23°C and 50% relative humidity. The supplied air was filtered by activated carbon.

Sampling was done 28 days after loading the chamber by means of Tenax TA, Multisorb and DNPH tubes performed. The resulting samples as well as the blank value were analyzed on VOC, aldehydes and carcinogens.

4 Results

4.1 TVOC

In accordance with DIN EN ISO 16000-6, for the determination of volatile organic compounds in indoor air about 5 litres of the chamber air are passed through a stainless steel adsorption tube filled with Tenax TA by means of a sampling device. In the laboratory, the tubes are thermally desorbed and the released substances identified by GC / MS analysis. As far as reference material standards are available, also a quantitative analysis can be made. The analysis of the sample was performed by the WESSLING environmental laboratory in Budapest.

Table 1: VOC-results (28 d-measurement)

Parameter (CAS Registry Number)	Group	CAS Registry Number	VOC-Concentration Test Chamber ($\mu\text{g}/\text{m}^3$)	Guidance Value ($\mu\text{g}/\text{m}^3$)
Ethylhexanol	VOC	104-76-7	4,6	
BHT (Butylated hydroxytoluene)	VOC	128-37-0	16,7	
2-Phenoxyethanol	VOC	122-99-6	29,5	
2-Butoxy ethyl acetate	VOC	112-07-2	11,4	
1-(2-Methoxymethylethoxy)- Propanol acetate	VOC	88917-22-0	10	
Sum of oxygenated hydrocarbons			72,2	
Caprolactam	VOC	105-60-2	79,7	
Benzophenone	SVOC	119-61-9	33	
Sum other compounds			112,7	
Somme VVOC (<C6)	VVOC		---	---
Somme TVOC (C6-C16)	VOC		152	1.000*
Somme SVOC (>C16-C22)	SVOC		33	---

* For classification A+

4.2 Aldehydes

For the detection of aldehydes in indoor air 50 litres of air are directed through a derivatizing absorption medium (2,4-dinitrophenylhydrazine). The aldehydes in the air form corresponding hydrazones. After elution with acetone quality and quantity are determined by HPLC.

The samples were analyzed by the environmental laboratory WESSLING, Hanover.

Table 2: Aldehydes-results (28 d-measurement)

Parameter	Concentration Test Chamber ($\mu\text{g}/\text{m}^3$)	Guidance Value ($\mu\text{g}/\text{m}^3$)
Formaldehyde	<2	10*
Acetaldehyde	10,3	200*

* For classification A+

5 Evaluation

5.1 Classification

The following criteria of the « Arrêté du relatif à l'étiquetage des produits de construction et de décoration pour ce qui concerne leurs caractéristiques d'émissions en substances volatiles polluantes » are available for the emission test:

Substance	C ($\mu\text{g}/\text{m}^3$)	B ($\mu\text{g}/\text{m}^3$)	A ($\mu\text{g}/\text{m}^3$)	A+ ($\mu\text{g}/\text{m}^3$)	Test Result
Formaldehyde	> 120	< 120	< 60	< 10	1,3
Acetaldehyde	> 400	< 400	< 300	< 200	10,6
Toluol	> 600	< 600	< 450	< 300	bld
Tetrachlorethylene	> 500	< 500	< 350	< 250	bld
Xylol	> 400	< 400	< 300	< 200	bld
Trimethylbenzene	> 2.000	< 2.000	< 1.500	< 1.000	2,4
1,4-dichlorobenzene	> 120	< 120	< 90	< 60	bld
Ethylbenzene	> 1.500	< 1.500	< 1.000	< 750	bld
2-Butoxyethanol	> 2.000	< 2.000	< 1.500	< 1.000	bld
Styrol	> 500	< 500	< 350	< 250	bld
TVOC	> 2.000	< 2.000	< 1.500	< 1.000	152

bld: below limit of detection

The product CLIPSO IMPRIME UV meets the criteria of classification A +.

6 Summary

Laboratoires WESS-LING S.A.R.L was contracted by CLIPSO PRODUCTION to perform an emission test chamber study of the product “CLIPSO IMPRIME UV (Lot: F11002793)” on the emissions of volatile organic compounds (VOCs) and aldehydes. The evaluation is done according to the « Arrêté du 19 avril 2011 relatif à l'étiquetage des produits de construction ou de revêtement de mur ou de sol et des peintures et vernis sur leurs émissions de polluants volatils ».

The product “CLIPSO IMPRIME UV (Lot: F11002793)” meets the criteria of the A + - Classification after 28 days.

Tested by  **WESSLING**

Jean-François Campens
Engineering Editor

Christopher Teichmann
Diplom-Ingenieur
(Graduated Engineer)